

Recommended paint systems for fuel storage steel structures

| System No. | Recommended Application | Primer | | Primer/Midcoat Primer | | Topcoat | | Total NKFK* |
|------------|-------------------------|--|-------|---|-------|--|-------|-------------|
| | | Generic Name Paint System Serial No | NKFK* | Generic Name Paint System Serial No | NKFK* | Generic Name Paint System Serial No | NKFK* | |
| 26 | tank indoor | Phenolic Epoxy BA140 | 150 | Phenolic Epoxy BA140 | 150 | | | 300 |
| 27 | tank indoor | Epoxy Epomarine Primer PC | 40 | Epoxy Epomarine PC100 Primer + Epomarine PC100 | 200 | Epoxy Epomarine PC100 Topcoat | 100 | 340 |

Note *NDFT: Nominal dry film thickness, ** : KANSI ALTAN's recommendation of paint system for expected durability , If other systems are required, please ask Kansai Altan representative!

Recommended paint systems for potable water storage steel structures

| System No. | Recommended Application | Primer | | Primer/Midcoat Primer | | Topcoat | | Total NKFK* |
|------------|-------------------------|--|-------|--|-------|--|-------|-------------|
| | | Generic Name Paint System Serial No | NKFK* | Generic Name Paint System Serial No | NKFK* | Generic Name Paint System Serial No | NKFK* | |
| 28 | tank indoor | Epoxy BA144 | 150 | Epoxy BA144 | 150 | | | 300 |
| 29 | tank indoor | Epoxy BA146 | 150 | Epoxy BA146 | 150 | | | 300 |

Note *NDFT: Nominal dry film thickness, ** : KANSI ALTAN's recommendation of paint system for expected durability , If other systems are required, please ask Kansai Altan representative!

Recommended paint systems for steel structures buried in soil/water

| System No. | Recommended Application | Primer | | Primer/Midcoat Primer | | Topcoat | | Total NKFK* | Expected Durability** | | | |
|------------|-------------------------|--|-------|--|-------|--|-------|-------------|-----------------------|--------|------|-----------|
| | | Generic Name Paint System Serial No | NKFK* | Generic Name Paint System Serial No | NKFK* | Generic Name Paint System Serial No | NKFK* | | Low | Medium | High | Very High |
| 30 | Im1, Im2 | Zinc Rich Epoxy BA69 | 60 | Epoxy BA960 | 300 | | | 360 | | | | |
| 31 | Im1, Im2 | Zinc Rich Epoxy BA69 | 60 | Epoxy BA124 | 300 | | | 360 | | | | |

Note *NDFT: Nominal dry film thickness, ** : KANSI ALTAN's recommendation of paint system for expected durability , If other systems are required, please ask Kansai Altan representative!